



# Fast Set 595

DRY SET PORTLAND CEMENT MORTAR



## PACKAGING

25 lb (11.4 kg) bags

## STORAGE

Store in a cool, dry location at a temperature between 40°F (4°C) and 90°F (32°C). Do not store in direct contact with the ground or concrete. Store out of direct sunlight and protect from weather and other damage

## DRYING & CURING


Allow freshly applied material to dry at least 24 hours before grouting or light foot traffic. Drying time may vary due to porosity of substrate and tile, climate, job conditions and should not take more than 24 hour at an ambient and surface temperature of 70°F (21°C) and 55% humidity. Material is fully cured in 28 days

## GROUTING

Grouting can be done within two hours of install.

## MATERIAL CALCULATOR

Visit the Sienna web site at [SiennaProducts.com](http://SiennaProducts.com) and click on the "Material Calculator" tab for recommended products and to calculate the amount of materials needed for each project. Always follow all manufacturers' recommendations and warranty information prior to any tile or stone installation.



Sienna Fast Set 595 is a fast setting mortar manufactured with a mixture of portland cement, graded aggregates and other proprietary additives to produce a high quality mortar. Sienna Fast Set 595 enables the install of tile and grout to be done within two hours, and is ready for foot traffic in four hours. Sienna Fast Set 595 is available in either white or gray color and complies with the requirements of ANSI A118.1. If used in conjunction with Sienna Acrylic Admix AX300, it will also comply with the requirements of ANSI A118.4 and A118.11.

FEATURES	BENEFITS
Walls & Floors	Ready to Grout in 2 Hours
Interior & Exterior	Foot Traffic in 4 hours
Residential & Commercial	Meets ANSI A118.1

## BASIC USES

Sienna Fast Set 595 is used as a non-modified mortar for interior and exterior application of most tiles and stones. Sienna Fast Set 595 can be used on floors and walls up to 3/16" thick in residential and commercial projects. Use Sienna Fast Set 595 any time tile and grout installs need to be done within two hours and open to traffic in four hours.

## RECOMMENDED SUBSTRATES

Properly prepared substrates includes: Cured concrete (28 days), portland cement mortar beds, brown coat, backer boards (per manufacturer's specifications), gypsum boards (dry interior walls only), masonry block, brick and porous stone.

## SURFACE PREPARATION

All surfaces to receive application must be structurally sound, clean and free of debris, dirt, dust, efflorescence, wax, grease, oils, curing agents, cleaning solutions, sealers, adhesive residues or gypsum-based underlayments, or anything that would hinder proper bond. Smooth or painted surfaces can be prepared by mechanical means such as sanding, scraping or using Sienna Gripping Primer. Dampen surface prior to application, but do not allow water to puddle. Substrate temperature must be within 45°F (7.2°C) and 85°F (29.4°C). For complete installation methods see the TCNA (Tile Council of North America) Handbook and ANSI A108.5.

## MIXING

Mix by hand or use a mixer of less than 300 rpm to avoid too much entrapped air. Add gradually one 25lb bag of Sienna Fast Set 595 to approximately 2¾ quarts (2.6L) of potable water or Sienna Acrylic Admix AX300 while mixing. Water or admix must be cool in temperature, clean and clear. Do Not use hot or warm water or admix. Mix material thoroughly to a smooth consistency. Do Not add additional water, admix or powder after mixing period. During application, occasionally stir the mixture to help maintain workability. After 30 minutes, mixture will harden and will no longer be usable.



# Fast Set 595

DRY SET PORTLAND CEMENT MORTAR

## CEMENTITIOUS SUBSTRATES

Cementitious substrates can be cleaned by mechanical means such as sanding, scraping or chipping. Smooth painted or waterproof cementitious surfaces can be prepared by mechanical means such as sandblasting, scraping or using Siena Gripping Primer. Dampen the surface prior to the application but do not allow water to puddle. Substrate deflection not to exceed L/360. For complete installation methods see the TCNA (Tile Council of North America) Handbook and ANSI A108.5.

## NON-CEMENTITIOUS SUBSTRATES

Use a cleavage membrane on surfaces with bonding problems, such as plywood or painted surfaces. For walls, apply a 3/8" to 3/4" thick layer of wire reinforced mortar bed, and for floors apply a minimum of 1 1/4" wire reinforced mortar bed. Let it set for at least 20 hours and then apply the dry-set mortar.

## TILE SUBSTRATES

Use Siena Gripping Primer over the existing tile and allow to dry (20 - 60 mins.) before applying mortar. Siena Acrylic Admix AX300 must be used with Siena Fast Set 595 to ensure proper bond. Existing tile must be sound, well bonded, clean and free of anything that would hinder proper bond or prevent adhesion. For complete installation methods see the TCNA (Tile Council of North America) Handbook and ANSI A108.5.

## APPLICATION

The size of the working area should be such to be covered with tiles within 10 - 15 minutes. Using the flat side of the notch trowel apply a tight, thin layer of mortar over the substrate. Then add more mortar and comb the material in one direction using the appropriate notch size to achieve 100% contact to the back of the tiles. Set the tiles over the mortar, applying firm pressure to flatten the ridges and assure good contact. Periodically check already placed tiles to verify that there is sufficient mortar transfer with the back of the tile. Back-butter the tiles if required. Align tiles immediately after their placement and clean any excess material with a damp sponge. Tiles that have been setting for more than 5 - 10 minutes should not be readjusted.

## LIMITATIONS

DO NOT apply Siena Fast Set 595 directly over wood or wood products, gypsum mortar beds, asphalt sheeting, vinyl covered wall board, Masonite, cement asbestos board, metal, glass, plastic or any dimensionally unstable substrate. DO NOT apply at temperatures below 45°F (7.2°C) or above 85°F (29.4°C). When hot, dry, or windy conditions exist, protection must be provided. The ambient and surface temperature must maintain the above requirements until fully dried. Material that is allowed to freeze may suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully dried (See Drying & Curing). DO NOT add any other materials to the mixture of the product without written approval from Siena, Omega Products International. DO NOT deviate in the mixing or application procedures contained in this, or any other Siena Product data sheets without written approval from Siena or Omega Products International. DO NOT use with green or red marbles as they may react with the mortar, warp and detach. For these moisture sensitive materials use Siena Epoxy Mortar & Grout.

## TECHNICAL DATA

Open Time at 73°F (23°C)	20 Minutes
Adjustability at 73°F (23°C)	20 Minutes
Bucket Life at 73°F (23°C)	30 Minutes
Compressive Strength ASTM C-109	>3,200 psi
Shear Bond ANSI A118.1	
Glazed Wall Tile	
2 Hours	>200 psi
4 Hours	>300 psi
24 Hours	>500 psi
Porcelain Tile	
2 Hours	>140 psi
4 Hours	>350 psi
24 Hours	>450 psi

## COVERAGE

Square Notch Trowel Coverage

1/4" x 1/4" x 1/4" (6 x 6 x 6 mm)	48 ft <sup>2</sup> (4.4 m <sup>2</sup> )
1/4" x 3/8" x 1/4" (6 x 9.5 x 6 mm)	37 ft <sup>2</sup> (3.4 m <sup>2</sup> )
1/2" x 1/2" x 1/2" (13 x 13 x 13 mm)	24 ft <sup>2</sup> (2.2 m <sup>2</sup> )

*Note: Values listed above are typical results for tests indicated and should not be considered specifications. Actual product performance will depend on job conditions, temperature, humidity and application methods.*

## EXPANSION & CONTROL JOINTS

Never apply Siena Fast Set 595 over any expansion or control joint. For more information regarding this types of joints see TCNA (Tile Council of North America) Handbook and EJ-171.

## TECHNICAL ASSISTANCE

Technical information is available on our web site at: SienaProducts.com, by calling Omega Products International at: 800.600.6634, or by email at: info@omega-products.com

## CLEANING

Cleaning may be accomplished with water immediately after use.

## SAFETY

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

## WARNING

Omega Products International, Inc., as a blender of processed material in the State of California, is required by Proposition 65 to warn that one or more of the components contained in this product, could contain chemicals known to the State of California to cause cancer, birth defects or other reproductive harm. The State of California (Proposition 65) requires this warning in the absence of definitive testing to prove that the defined risks do not exist. We believe this product complies with all other applicable state and federal laws and regulations governing manufacturing, distribution and intended use. User is solely responsible for the legal disposal of this container and its contents.

## KEEP OUT OF REACH OF CHILDREN

## Disclaimer

Omega Products International [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond the

control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his or her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.